

PAPER BOARD WITH POLYETHYLENE - CUPSTOCK BOARD



ITEM	BASIS WEIGHT THICKNESS		SMOOTHNESS	D65 BRIGHTNESS	STIFFNESS		DIRT COUNT			MOISTURE
					mN·m CD	mN·m MD	(0.3-1.5)mm ²	> 1.5-2.5mm ²	> 2.5mm ²	
UNIT	g/m ²	µm	s	%						%
TEST METHOD	GB/T 451	GB/T 451	GB/T 456	GB/T 7974	GB/T 22364		≤			GB/T 462
	140±5	190±10	≥8	80±5	≥1.2	≥2.0	40	4	0	6.0±2.0
	150±5	205±10	≥8	80±5	≥1.2	≥2.0	8.2	4	30.12	6.0±2.0
	160±5	215±10	≥8	80±5	≥1.2	≥2.0	8.2	4	30.12	6.0±2.0
	170±5	225±10	≥8	80±5	≥1.2	≥2.0	40	4	0	6.0±2.0
	180±6	240±10	≥8	80±5	≥1.2	≥2.0	40	4	0	6.0±2.0
	190±6	250±10	≥8	80±5	≥1.8	≥3.6	40	4	0	6.0±2.0
	200±6	265±12	≥8	80±5	≥1.8	≥3.6	40	4	0	6.0±2.0
	210±7	275±12	≥8	80±5	≥1.8	≥3.6	40	4	0	6.0±2.0
	220±7	290±10	≥8	80±5	≥3.0	≥6.0	40	4	0	6.0±2.0
	230±8	300±12	≥8	80±5	≥3.0	≥6.0	40	4	0	6.0±2.0
	240±8	315±12	≥8	80±5	≥3.0	≥6.0	40	4	0	6.0±2.0
	250±8	325±12	≥8	80±5	≥3.0	≥6.0	40	4	0	6.0±2.0
	260±8	340±15	≥8	80±5	≥4.5	≥9.0	40	4	0	6.0±2.0
	270±10	350±15	≥8	80±5	≥4.5	≥9.0	40	4	0	6.0±2.0
	280±10	360±12	≥8	80±5	≥4.5	≥9.0	40	4	0	6.0±2.0
	290±10	375±15	≥8	80±5	≥4.5	≥9.0	40	4	0	6.0±2.0
	300±10	390±15	≥5	80±5	≥4.5	≥9.0	40	4	0	6.0±2.0
	310±10	400±15	≥5	80±5	≥6.5	≥13.0	40	4	0	6.0±2.0
	320±12	415±15	≥5	80±5	≥6.5	≥13.0	40	4	0	6.0±2.0
	330±12	425±15	≥5	80±5	≥6.5	≥13.0	40	4	0	6.0±2.0
	340±14	440±15	≥5	80±5	≥6.5	≥13.0	40	4	0	6.0±2.0
	350±14	450±15	≥5	80±5	≥6.5	≥13.0	40	4	0	6.0±2.0



Typical Values

Características Principales / Características do produto

Multilayer paperboard, double coated on the topside, high bulk and cream backside
 Cartón multicapa, doble cara en la parte superior, high bulk y reverso color crema
 Cartão multicamadas, dupla face na parte superior, high bulk e verso creme

CONTACT US

sales@catrading.com